

Lignodur Grenodecor 236



Environmental decorative woodstain on an acrylate basis



Color System

Field of application

For environmentally friendly, diffusible, transparent and colored woodstains with a natural wooden appearance, primarily for interior areas, but also on exterior wooden surfaces. Can be used on non-dimensionally stable, limited dimensionally stable, and dimensionally stable wooden components made of hardwood and coniferous wood, e.g., wooden cladding, paneling and windows.

Properties

- Water-based, low-emission and low-pollutant
- Acrylate-based
- For indoors and outdoors
- Quick drying
- Highly diffusible
- Good penetration properties
- Matt
- Block resistant
- One-pot system
- Tested according to AgBB requirement schemes
- Complies with EN 71-3 Safety of toys, resistant to saliva and perspiration
- Easy application, thanks to low resistance when brushing on

Material description

Color shades	Scale no.	Description
	-	0100 transparent ¹⁾
	09.LA.03	1410 oak
	09.LA.02	1411 pine
	21.LA.03	3410 mahogany
	03.LA.08	7410 pebble
	75.LA.02	7411 graphite
	15.LA.03	8410 nutbrown
	15.LA.02	8411 chestnut
	12.LA.05	8412 teak

Material description

Color shades	Scale no.	Description
	18.LA.04	8415 rosewood
	03.LA.03	9410 ebony
	03.LA.01	9510 chalk white
	¹⁾ May only be used indoors, please refer to the information below Notes. Additional color shades from the Brillux Color System.	
Base material	Acrylate copolymer dispersion	
VOC	EU limit for this product (Cat. A/e): 130 g/l (2010). This product contains max. 1 g/l VOC.	
Constituent substances	Acrylic-copolymer-dispersion, titanium dioxide (depending on the shade), inorganic/organic pigments (depending on the shade), silicates, water, additives and preservatives (benzothiazolinone and sodium pyrithione).	
Density	Approx. 1.0–1.1 g/cm ³	
Packaging	Standard: 750 ml, 3 l, 10 l Color System: 750 ml, 3 l, 10 l	

Use

Thinning	On very absorbent substrates, e.g. for the first coat, thin with up to 3% water.
Tinting	All colors can be mixed with one another without limitations.
Compatibility	Do not mix with other types of materials.
Application	Stir thoroughly before use. Evenly brush Lignodur Grenodecor 236 using a paintbrush with synthetic bristles, e.g. Uni-Plus Paint Brush. Alternatively, Lignodur Grenodecor 236 can be applied by spray application. In that case, the surfaces are subsequently to be smoothed by brush. More information on spray application is provided in the following "Spray data" table.
Consumption	Approx. 70–80 ml/m ² per layer. Determine the exact consumption by means of a test application on the object to be coated.
Application temperature	Do not apply if air or object temperature is below +5°C.
Tool cleaning	Clean tools immediately after use with water and soap.

Use

Spray data

Spray system	Nozzle	Spray angle	Supply air / air quantity	Material pressure / material quantity	Thinning	Cross-spraying ⁴⁾
Low pressure ¹⁾	Yellow front end ²⁾	–	50–75%	Ring setting 5–6	unthinned	1
Airless	0.008 inch	40°	–	60 bar	unthinned	1
Battery-Airless ³⁾	0.008 inch	–	–	regulator Level 5 (110 bar)	unthinned	½

The data is based on substrate and ambient temperatures of +20°C.

¹⁾ Information relating to XVLP technology with Wagner FinishControl FC 3500 or FC 5000.

²⁾ StandardSpray spray attachment (yellow) for all standard enamel paints and woodstains. Also keep the nozzle clean during application. Remove dry paint material with a soft brush. Please follow the equipment manufacturer's instructions.

³⁾ Information relating to the use of the SprayPack 18 V Select 3344 spraying system.

⁴⁾ The areas are to be brushed after spray application to achieve a smooth surface.

Drying (+20°C, 65% relative humidity)

Dust dry after approx. ½ hour. Recoatable after approx. 3 hours. Allow for longer drying time if the temperature is lower and/or the humidity is higher.

Storage

Store in a cool, dry and frost-free place. Reseal opened containers tightly. Only recycle completely empty containers. Dispose of liquid material residue at a collection point for old paint.

Declaration

Note Contains preservatives
Do not inhale spray mist

Product code BSW20
Comply with the specifications in the current safety data sheet.
Information for people allergic to isothiazolinone can be obtained by calling +49 251 7188-403

Substrate preparation

- The substrate must be solid, dry, clean, with good adhesiveness, load-bearing and free from separating agents.
- The BFS Leaflet no. 18 specifies that the moisture content for dimensionally stable components must be limited to 15%. For non-dimensionally stable components and components with limited dimensional stability, the moisture content must not exceed 18%.
- Remove grayed wood down to the load-bearing wood layers.
- Hazardous particles and vapors may be released while reworking or removing old paint coats, e.g. as a result of sanding, paint removal by heat gun, etc. Perform such work in well ventilated areas only and ensure the use of appropriate protective equipment (including respiratory protective equipment) as required.
- Also see BFS Leaflet no. 18, 4 and 5, as well as VOB Part C, DIN 18363, Paragraph 3.

Interior coats on wood

Substrates	Prime coat	Intermediate coat	Top coat
Untreated wooden components and wood-based materials, indoors	Lignodur Grenodecor 236	If necessary, Lignodur Grenodecor 236	Lignodur Grenodecor 236
Wooden components and wood-based materials with intact woodstain coating, indoors	If necessary, repair damaged areas with Lignodur Grenodecor 236		

Exterior coats on non-dimensionally stable and limited dimensionally stable wooden components

Substrates	Impregnation ¹⁾	Prime coat	Intermediate coat	Top coat
Untreated, dimensionally stable, limited dimensionally, and non-dimensionally stable wooden components, in exterior areas, e.g., wooden paneling with tongue and groove (e.g. roof soffits), pergolas, shutters, fences	Lignodur Contrabol Aqua 250	Lignodur Grenodecor 236	Lignodur Grenodecor 236	Lignodur Grenodecor 236
Wooden components with an intact woodstain coat	Raw wooden surfaces with Lignodur Contrabol Aqua 250	If necessary, Lignodur Grenodecor 236		

¹⁾ Follow the instructions in BFS Leaflet No. 18, Sections 6 and 7.2.1.

Protective measures	Keep out of reach of children. Use protective glasses and the combination filter A2/P2 for spraying. Use the dust filter P2 during sanding. Ensure proper ventilation during application and drying. Avoid eating, drinking and smoking during application. Upon contact with eyes or skin, immediately rinse thoroughly with water. Ensure that the material does not enter the sewage system, waters or soil.
Sand the substrates	Sand the surfaces between work steps.
Avoid contact with plasticizers	Do not allow the surfaces to come into contact with plastics containing plasticizers, e.g. sealing profiles.
Avoid “paint-on-paint” contacts	Water-based enamel paints exhibit thermoplastic behavior. As a consequence, “paint-on-paint” contacts must be avoided.
Check old coatings	Check old woodstain coatings for adhesion, for example by scratching the substrate or applying then removing sticky tape. Applying a wet cloth to the surface additionally clarifies whether the coating and/or the wood is suitable for coating build-up. If a dark, damp spot appears on this part of the wood after a brief period, then the surface needs to be sanded back to the load-bearing wooden layer.
Assess woodstain color shade	The various kinds of wood and existing intact woodstain coatings affect the woodstain color shade due to intrinsic color and absorbency. For this reason, we recommend applying a test coat in advance.
Do not use colorless build-up outdoors	Colorless woodstain coats are not suitable as a sole coating build-up for use in exterior areas due to their insufficient UV protection.
Wood constituents	If there is a risk of soluble wood constituents bleeding through white or light woodstain coatings, we recommend using opaque coating systems, as required.
Shelf life of woodstain coating	The shelf life of a woodstain coating depends on countless factors, e.g., the construction and the general impregnation and priming of the (specified) components. To maintain the woodstain coating, we recommend performing checks at regular intervals, but after 2–3 years at the latest, and if necessary, maintenance of the woodstain coating is to be performed, especially in areas exposed to weathering.
Wood-based panels for outdoors	In accordance with the current state of the art, wood-based panels are only conditionally suited for coating in exterior areas. Also refer to BFS Leaflet No. 18, Paragraph 2.2.3. A coating recommendation can only be provided on a case-by-case basis under consideration of the material type and quality, construction, and climatic conditions. Please contact the Brillux Consulting Service if you require assistance in this context.
Cleaning and maintenance	For cleaning the painted surfaces, use a clean, soft cloth, dry or damp, without abrasive, solvent-based or caustic agents. Clean without applying excessive pressure (do not polish the surfaces). Perform a test cleaning beforehand in an inconspicuous area. Only clean surfaces that have completely dried and cured.
Further information	Follow the instructions on the data sheets of the products used.

Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com